

Mastic Asphalt Terrazzo Tiles

Description

Shield Membrane Terrazzo Tile provides a durable elegant look to any project. It is available in polished finishes, and produced to meet ISO 9001 and 14001, quality assurance and environmental standards.

For individuality, different aggregate colours are available, and fully customisable to meet a desired look.

It is offered across all paving flooring elements with slip and skid-resistant properties.

All Shield Membranes Terrazzo Tiles are fully tested to the appropriate standards in the UK and CE marked in accordance with the latest legislation. The tiles are hard-wearing, strong and durable.



TECHNICAL INFORMATION

Testing Method

Weight (kg):	36			
Length:	596	600		
Width	596	600		
Thickness:	37.5	42.5		
Work Dimensions(mm):	598x598x50			
Nominal Dimensions (mm):	600x600x50			
Tolerances on work Dimensions (mm):	Length ±2mm, width ±2mm, thickness 2.5mm			
Indentation Test	500mm ² pin, 40 °C, 30 minutes: 0.11mm 100mm ² pin, 40 °C, 120 minutes: 0.25mm 100mm ² pin, 22 °C, 300 minutes: 0.08mm			
Load Test (KN):	Point Load 25	Shear Load 17	Triaxle Load 27	BS EN 12825
Abrasion Resistance (mm):	16			BS EN 1338:2003
Compressive Strength (N/mm ²):	17.0			BS EN 12504-1:2009
Slip Resistance PVT:	Wet 41	Dry 69		BS EN 1338:2003
Thermal Conductivity W/mk:	0.50			
Water Absorption (%)	0.4			BS ISO 1920 ASTM C1585
Reaction to Fire:	Broof (T4)			
Specific Gravity:	2.0 - 2.4			

The evolution of new product design is continuous and information is subject to change without notice. Customers should check with the supplier to ensure that they have the latest details. Shield Membranes reserve the right to amend the technical information as deemed necessary and in accordance with the relevant national and international standards without notice.

0207 740 9279 | www.shieldmembranes.com | info@shieldmembranes.com

You're protected with Shield on your side™

Whilst every care is taken to see that the information given in this literature is correct and up to date it is not intended to form part of any contract or give rise to any collateral liability, which is hereby specifically excluded. Intending purchasers of our materials should therefore verify with the company whether any changes in our specification or application details or otherwise have taken place since this literature was issued.